Technical specifications

Marmoleum sheet meets the requirements of EN-ISO 24011 Marmoleum Decibel sheet meets the requirements of EN 686



			Marmoleum sheet Walton, Concrete, Piano, Cocoa, Slate	Marmoleum Decibel sheet Walton, Concrete, Piano, Cocoa, Slate		
í v	Total thickness	EN-ISO 24346	2.5 mm	3.5 mm		
	Surface finish		topshield ²	topshield ²		
in min	Domestic use	EN-ISO 10874	Class 23, heavy	Class 23, heavy		
i iii	Commercial use	EN-ISO 10874	Class 34, very heavy	Class 33, heavy		
hi in	Light Industrial use	EN-ISO 10874	Class 43, heavy	Class 41, moderate		
	Collection size		78 colours	78 colours		
T S	Roll width	EN-ISO 24341	2.00 m	1.95 / 2.00 m		
3	Roll length	EN-ISO 24341	≤ 33 m	≤ 33 m		
ß	Total weight typical value	EN-ISO 23997	2900 g/m²	3100 g/m²		
Ģ	Residual indentation	EN-ISO 24343-1	≤ 0.15 mm	≤ 0.30 mm		
	Typical value		~0.08 mm	~0.20 mm		
6	Castor chair continuous use	ISO 4918/ EN 425	Suitable for office chairs with castors			
- -	Light fastness	EN-ISO 105-B02	Method: 3 blue scale > 6			
2	Flexibility	EN-ISO 24344	ø 40 mm	ø 40 mm		
 	Resistance to chemicals	EN-ISO 26987	Resistant to diluted acids, oils, fats and to the conventional solvents. Not resistant to prolonged exposure to alkalis.			
ľ	Bacteriostatic properties*		Marmoleum has natural bacteriostatic properties which are confirmed by independent laboratories, even against the bacteria MRSA.			
\$	Cigarette resistance	EN 1399	There is no melting of the surface by cigarettes. Marks left on Marmoleum as a result of stubbed-out cigarettes can be removed.			
. K.E.	Slip resistance	DIN 51130	R9 Slate R10	R9 Slate R10		
٢	Acoustical impact sound reduction	EN-ISO 717-2	≤5 dB	18 dB Marmoleum with polyolefine foam backing. All items available as make to order.		
	Indoor Air Emissions: TVOC at 28 days	EN ISO 16000-9	< 50 µg/m³	< 50 µg/m³		
LCA	Life Cycle Assesment**		LCA is the foundation for securing the lowest environmental impact.			
© 0	Creating better environments					
	1		Marmoleum is pr	roduced CO ₂ neutral.		
\prec	renewable electricity		Marmoleum is manufactured using 100% electricity from renewable sources.			
			Marmoleum and Marmoleum Decib	el are made of 94-98% natural materials.		
	natural materials (e.g. linseed oil, jute, tree resin, wood flour, limestone)		Marmoleum contains PEFC certified wood flour.			
			Marmoleum Cocoa additionally contains natural cocoa shells, a production residue of regional Dutch cocoa productio			
			Marmoleum and Marmoleum Decibel are free of PVC, PET, synthetic rubber and plasticizers.			
			Marmoleum is REACH compliant.			
0	recycled content		Marmoleum contains recycled content.			
(111)	Application on underfloor heating		yes	yes		

CE	Product code	EN 14041	0100201-DoP-306	0100207-DoP-306
Brrst	Reaction to fire	EN 13501-1	C _n -s1	C _{ff} -s1
Kan DS	Slip resistance	EN 13893	$\text{DS-}\mu \geq 0.30$	DS-µ ≥ 0.30
Ż	Body voltage	EN 1815	$\leq 2 \text{ kV}$	≤ 2 kV
믤	Thermal conductivity	EN 12524	0.17 W/m·K	0.17 W/m·K

* Marmoleum sheet can be installed nett fit, or with a welding rod in the seam. Both are proven hygienic solutions.
** Application of Marmoleum sheet can help maximize contribution in the project/building for LEED qualification.

All Forbo Flooring Systems' sales organisations worldwide have a certified Quality Management System in accordance with ISO 9001. All Forbo Flooring Systems' manufacturing operations have a certified Environmental Management System in accordance with ISO 14001. The Life Cycle Assessment (LCA) of Forbo Flooring Systems' products is documented in individual Environmental Product Declarations (EPD's) which can be found on all of our websites.





